


# PMC Comparison of Firing Options

This chart shows the 7 different firing scenarios for the three products in the silver Precious Metal Clay line.



PMC 1650° F / 900° C for two hours

PMCT 1650° F / 900° C for 10 minutes  
1560° F / 850° C for 20 minutes  
1470° F / 800° C for 30 minutes

PMC3 1290° F / 700° C for 10 minutes  
1200° F / 650° C for 20 minutes  
1110° F / 600° C for 45 minutes